## **CLAIMS**

A polymer-electrolyte fuel cell, comprising:
an electrolyte membrane-electrode assembly
comprising a polymer-electrolyte membrane, and a pair of gas diffusion electrodes sandwiching said polymer-electrolyte
membrane;

a first electroconductive separator having a gas channel for supplying an oxidant gas to one of the gas-diffusion electrodes of said pair; and

a second electroconductive separator having a gas channel for supplying a fuel gas to the other of the gas-diffusion electrodes of said pair; wherein

the polymer-electrolyte fuel cell is characterized in that

at least one of said first electroconductive separator and said second electroconductive separator comprises a metal substrate and an electroconductive resin layer provided on said metal substrate and contacting said electrolyte membrane-electrode assembly, and

said electroconductive resin layer comprises a resin having water-repellant or basic radicals, and an electroconductive particulate substance.

2./ The polymer-electrolyte fuel cell in accordance with claim /, wherein said electroconductive particulate

substance comprises a carbon powder having a specific surface area of less than  $100~\text{m}^2/\text{g}$ .

3. The polymer-electrolyte fuel cell in accordance with claim 1, wherein said electroconductive particulate substance comprises vitreous carbon.

4. The polymer-electrolyte fuel cell in accordance with claim 1, having, between said metal substrate and said electroconductive resin layer, a layer including at least one selected from the group consisting of: metallic Zn, metallic Sn, metallic Al, Cr-containing compounds, Mo-containing compounds and W-containing compounds.

51 A1